

I. PRODUCT & MANUFACTURER INFORMATION

I.1 PRODUCT ID

COLLECTION

BASE COLOUR

PRIMEFIX Q

SEMI-TRANSPARENT

I.2 MANUFACTURER

CREATE S.p.A.

Via Venezia, 14/A – 41034 Finale Emilia (MO) – Italy

Tel. +39 0535 761811 fax. +39 0535 761800

www.createspa.com - e-mail: create@createspa.com

I.3 PRODUCT DESCRIPTION AND INTENDED USES

Primefix Q is acrylic water based sealer for interior walls and **meets the tightest international regulations about health, safety and environmental impact**

I.4 QUALITY ASSURANCE DATA

SPECIFIC GRAVITY (WATER=1.00)	1.3 – 1.4 (25°C)
SOLIDS PERCENT BY WEIGHT	50 – 55 %
V.O.C.	Max. 30 gr/lt
VISCOSITY (BROOKFIELD)	Max. 8000-14000 cps (25°C)
PH RANGE	8.0 – 9.0
SAFETY INFORMATION	Do not take internally. Keep far from children. Refer to Material Safety Data Sheets for detailed information.
SHELF LIFE	24 months for neutral base (from date of production, see batch ID), when stored in tightly closed cans at temperature ranging between 5 °C and 40 °C.
PRECAUTIONS	Keep from freezing and prolonged direct sun irradiation. Allow adequate ventilation.

2. HOW TO APPLY

2.1 INSTALLATION CONDITIONS

- Installation area must be clean and free of dust. Sufficient lighting must be provided.
- Environment and substrate temperatures should be between 10 °C and 40 °C (50 °F – 100 °F). The substrate must be dry to touch.
- Do not apply finishes if moisture content of surface is above 15%.
- Surfaces should be clean, dry and free of dust, dirt, mildew, wax, wallpaper paste, loose paint, soap and any other foreign matter or contaminants.
- For concrete and masonry substrates ensure that they have cured a minimum of 28 days.
- Mask ceilings, floors, doors, windows and other adjacent surfaces using a low adhesive masking tape to prevent overpaint.

2.2 SUBSTRATE PREPARATION

The substrate shall be smooth/non porous and prepared according to general criteria for getting the proper foundation for performance and application of conventional top quality water-borne paints. Make good any cracks and imperfections with a suitable plaster type filler. When dry, rub down and dust off to get a smooth surface. For badly damaged surfaces, cross lining may be necessary.

2.3 PRODUCT PREPARATION

- Stir thoroughly before use.
- Do not add solvents, thinners, reducers, oils or mix with solvent-based colorants or paints.

2.4 APPLICATION EQUIPMENT

The best results are obtained using a short pile or a synthetic bristle brush. Clean the application tools with water only, immediately after use.

2.5 APPLICATION GUIDELINES

- Apply one even coat of basecoat for Primefix Q using a short pile roller or a synthetic bristle brush covering the whole surface.
In case of particularly weak or dusty surfaces, apply one coat of Fractalis Primefix wet on wet till the complete impregnation of the surface, wait until touch dry (1-2 hours) and apply Fractalis Primefix Q.
- Wait 2-3 hours until touch dry

2.6 APPLICATION PARAMETRES

THINNING	None.
MILEAGE – SPREADING RATE	5-6 sqm/lt
DRYING TIME (25°C / 77°F, 50% R.U.)	Touch dry: 2 – 3 hours (drying time may vary depending on environmental temperature, humidity, type of substrate and film thickness).

2.7 MAINTENANCE AND REPAIR

Slightly dirty surfaces can be carefully washed with mild neutral cleansers. Avoid using alkaline and/or alcohol/solvent based detergents. Dirt, grime and stains that cannot be removed by standard maintenance practices as well as damaged areas should be repainted.

LIMITED WARRANTY

The Manufacturer warrants that the products supplied will be free of defects and conform with published Quality Assurance specifications and standards (see QAP). Notwithstanding, they do not exempt the user from employing the product correctly in terms of storage, handling, usage and waste management. In particular, the substrate preparation, application technique and environment conditions of use are beyond the control of Manufacturer. Therefore, the liability and obligations herewith shall be limited to the replacement of defective merchandise. For any further detail please refer to Sales and Quality Assurance Specifications.