

Strikolith Lightweight Plaster LUNA O2

Product Name:

Strikolith Lightweight Plaster LUNA O2

Composition:

A high quality, factory-prepared lightweight decorative plaster based on high-grade binding agents combined with additives and fillers to improve its working properties. Grain sizes: 0.8 mm and 1.2 mm.

Properties:

Strikolith Lightweight Plaster Luna O2 is extremely lightweight, odourless and scratch and impact resistant. Strikolith Lightweight Plaster Luna O2 distinguishes itself from other decorative plasters by the following unique properties:

- Extremely lightweight
- Extremely easy to apply
- Low usage
- Extremely high filling properties
- Even grain structure
- Extremely matt end result
- Health & Safety and user-friendly

Colors:

White and other colours in accordance with the Strikolith colour pallet..

Use:

Strikolith Lightweight Plaster Luna O2 is applied indoors as a high quality decorative plaster with a uniform, flat, matt and slightly open final structure. The lightweight properties of Luna O2 give a big advantage in the entire application process. Gives a unique matt appearance with both light and dark colours.

Technical data:

- S.G.: ca. 1.0 g / cm³
- Viscosity: ca. 250 Pa.s.
- pH-value: ca. 8.

Surface preparation:

Thoroughly remove existing loose plaster and layers of paint. First remove grease deposits and other contaminations with Strikolith Strikoclean. Repair superficial damage and plaster over with Strikolith FP200 Hechtgips (Adhesive gypsum). Always allow repairs to fully dry.

Surfaces:

First treat powdery, variably absorbent, strongly absorbent and gypsum surfaces (e.g. plaster blocks or gypsum seams/joint fillers) with Strikolith Deep Primer. Also with colour application, pretreat the surface with Strikolith Deep Primer. Pretreat ready-made surfaces with Strikolith Primer outdoors, in the colour of the final finish. If the surface is contaminated, apply Strikolith Isovoorstrijk (Iso-primer).

General Processing:

Mix Strikolith Lightweight Plaster Luna O2 thoroughly while adding no more than 0.5% clean tap water (45 ml / ¼ cup). Apply with a uniform grain thickness using a stainless steel trowel. Then distribute the grains properly and evenly using a hard plastic trowel, afterwards immediately 'touch up' the decorative plaster (check and smooth over). The unique properties and composition of Strikolith Lightweight Plaster Luna O2 result in a shorter drying time. Particularly with colour application, the various treatments of the final layer must be made quickly one after the other. Immediately clean tools with water after use.

Consumption:

Grain size 0.8 mm = ca. 1.0 kg per m².
Grain size 1.2 mm = ca. 1.3 kg per m².

Strikolith Lightweight Plaster LUNA O2

Packaging:

9 kg in kunststof emmer.

Storage:

Can be kept in a cool, frost-free and airtight place for 2 years.

Safety:

It is recommended to properly protect the eyes and skin using personal protective equipment while applying decorative plasters. If decorative plaster comes into contact with the eyes, immediately rinse with copious amounts of clean water (for about 15 mins.). Afterwards consult a doctor.

Particularities:

Before use, thoroughly mix several buckets of Strikolith Lightweight Plaster Luna O2 with each other. Building components that are not being treated with Strikolith Lightweight Plaster Luna O2 must be protected beforehand using paper and masking tape. Remove immediately after applying Strikolith Lightweight Plaster Luna O2. Do not apply under a surface and ambient temperature of + 5° C or if frost is expected.